

# TECHNICAL DATA SHEET

## POLYLACK PRIMER

### Description

Fast-drying anti-corrosion primer based on alkyd-resin and zinc phosphate.

### Use

It is used to protect metal surfaces- steel structures, machinery, gates, etc - from corrosion; in addition to general use, it may be used as a primer for Polylack A and Polylack W fire protection paints; with suitable top-coat paint up to corrosion category C3.

SPECIFICATIONS		
Colour	grey	
Solids content	48 ± 2% by vol.	
Density	1,58 - 1,68 g/cm <sup>3</sup>	
Drying	average drying time at 23°C, layer thickness 60 µm	
	touch dry	10 min
	handle dry	2 hours
	recoatable	2 hours
Theoretical consumption	0,15 kg /m <sup>2</sup> /50 µm	
Surface preparation	EN ISO 8501-1 Sa 2,5 grad, the surface to be painted must be dry, grease- and dust-free	
Application	brushing, rolling, spraying	
Dilution	by aromatic solvent	
Processing	between +5°C and +30°C , relative humidity up to 65 % the surface temperature to be painted is 3°C above the dew point	
Storage	12 months from the date of manufacture in the original factory packaging	
Packing	25 kg metal can	

### Safety regulations

Physical, toxicological, ecological and safety data and specifications relating to the safe use of the product are set out in the Safety Data Sheet and the requirements contained therein must be followed.